

Instructions for Hardrock Refinishing Diamond Powder RP1000-RP4000 Series

Diamond Powder is made into slurry and buffed into marble and limestone to produce a natural, high sheen for renewing and maintaining the shine on natural marble, limestone and terrazzo floors.

EQUIPMENT AND MATERIAL:

1. 175 to 300 RPM floor machine
2. Natural Hair Pad
3. Easy Mask or Surface Mask Tape, or Pre-Taped Drop Cloth.
4. Wet vac, mop, bucket, sponge, rags, etc.

Note: Directions are the same for each Series; however, please note:

Step 1 (RP1000 Series) is equal to a 200 grit finish.

Step 2 (RP2000 Series) is equal to a 400 grit finish.

Step 3 (RP3000 Series) is equal to an 800 grit finish.

Step 4 (RP4000 Series) is equal to an 1800 grit finish.

SAMPLE TESTING: Before using, always test each surface to be treated in a small inconspicuous area to insure the desired results will be achieved. Consult supplier for further information and precautions, including Material Safety Data Sheets.

INSTRUCTIONS:

1. Protect adjoining surfaces such as carpeting with Easy Mask or Surface Mask Tape, or Pre-Taped Drop Cloth.
2. Plan to polish seconds of a maximum of 10 to 15 square feet at a time.
3. Lightly wet an area about the diameter of the buffing pad with water.
4. Spread approximately one (1) scoop of polishing powder in the wetted area.
5. Buff the desired area with the Natural Hair Pad. Stop and check the floor periodically to see if the desired shine has been achieved.
6. Once desired shine has been achieved, rinse the area with clean water, wet vac off excess slurry, and damp mop with Hardrock No Rinse Neutral Cleaner.

***Note- Always Keep Powder Wet, add Powder as Needed.**

CAUTION:

Contains acid. Harmful if swallowed or inhaled. Keep out of reach of children. Protect all areas that may be damaged by acid with Easy mask tape or Pre-taped drop cloth. Always wear appropriate personal equipment. Read MSDS for further information and precautions. The most predominant chemical in this product is Potassium Oxalate which is CAS# 583-52-8.